

# **APPROVAL SHEET**

MESSRS		
BRAND	Ciblénergie	
PRODUCT	3.0V LITHIUM-MANGANESE BUTTON CELL	
MODEL	CR2450	
PREPARED BY	PASION HE	
APPROVED BY	ZHANG XUE HUI	
DATE	JAN. 18, 2006	



## 1. **[SCOPE]**

This specification applies to the following 3.0v lithium button cell CR2450

# 2. **[RATINGS]**

TABLE I:

ITEM		UNIT	SPECIFICATIONS	CONDITIONS	
Nominal voltage		V	3.0	Standard discharge	
Nominal capacity		mAh	600	Standard discharge	
Instantaneous short–circuit current		mA	≥250	Time≪0.5 second	
Off-load voltage		V	≥3.30		
Storage temperature		°C	0~35		
Standard weight		g	6.1	Unit cell	
Service	Initial	Continuous d	Continuous discharge with load 7.5kΩ, till 2.0v		
output	After 12 months storage	Standard	1600 h	end-voltage at 20~25℃	

#### TABLE II:


ITEM	CONDITIONS	CHARAC	TERISTICS
Thermal durability	Kept for 20 days at $60^{\circ}C\pm 3^{\circ}C$ , then continuously discharge with 7.5k $\Omega$ load till 2.0v end-voltage	Standard	1600 h
Self-discharge rate	Stored for 12 months at normal temperature and humidity	Ŵ	5%

### 3. [PERFORMANCE AND TEST METHODS]

Unless otherwise stated, all the testing is carried out under the condition: environmental temperature,  $20^{\circ}C \sim 25^{\circ}C$ ; environmental humidity,  $65 \pm 20\%$ . Please refer to Table III

## 4. **[SUGGESTIONS AND CAUTIONS]**

- 4.1 Install batteries correctly.
- 4.2 Ensure the contact points to be clean and conductive.
- 4.3 Do not mix different types, different brands batteries to serve together.
- 4.4 Do not heat, recharge the batteries.
- 4.5 Do not dispose of the batteries in fire.
- 4.6 Keep away from the small children, if swallowed promptly see doctor.
- 4.7 Pay attention to the producing date.




#### TABLE III:

No	ITEM	TEST METHODS	STA	ANDARED
1 Dimensions	Dimensions	Using vernier caliper (accuracy≥0.02) while	Diameter	24.5 (-0.20) mm
•	Dimensions	avoiding short-circuit	Height	5.0 (-0.20) mm
2	Off-load voltage	Using multimeter (accuracy $\geq$ 0.25%) internal resistance $\geq$ 1M $\Omega$		≥3.30v
3	Instantaneous short-circuit current	Time of short-circuit should be less than 0.5 second and avoid repeated test within half an hour	/\\	≥250 mA
4	Appearance	Eyeballing	Bright, cle leakage, Ar	an, no rust, no nd no flaw
5	Capacity	Continuously discharge for 8 hours with load 7.5k $\Omega$ , temperature at 20~25°C, humidity at 65±20% till 2.0v end-voltage (for fresh battery only: within 3 months )	7.11	≥1690 h
6	Vibration test	Put battery on the platform of the vibrations machine, start the machine and adjust the frequency form 10 times per minute to 15 times per minute. keep it running for an hour	Characteris	stics keep stability
7	Leakage at high temperature	Stored under temperature (60 $^\circ\!{\mathbb C}$ ) for 20 days	No lea	kage allowed
8	Over discharge Test	After 2.0v end-voltage, continuously discharged for 5 hours	No lea	kage allowed

# 5. **CUTAWAY DIAGRAM OF 3.0V LITHIUM MANGANESE DIOXIDE BUTTON CELL**


## Cutaway Diagram of 3.0V Lithium Manganese Dioxide Button Cell





# 6. [DISCHARGE CHARACTERISTICS]





0

7.5KΩ

#### 规格 SPECIFICATIONS

型 号 Model	CR2450	尺 寸 Dimensions(mm)
标称电压 Nominal Voltage	3(V)	
标称容量 Nominal Capacity	600(mAh)	(
标准电阻 Load Resistance	7.5(K Ω )	
重量 Weight	6.1(g)	#24 5-52 #21 5-62 #21 7-62
使用温度 Using Temperature	-20°C~60°C	



